

Technical Data Sheet

GEHR PVC-C®

PLASTICS ENGINEERED BY



I. Physical Properties¹⁾

| | Test method | Unit | Value |
|---|-------------|-------------------|-------|
| 1. Specific gravity (ρ) | ISO 1183 | g/cm ³ | 1,52 |
| 2. Water absorption ⁹⁾ | ISO 62 | % | 0,5 |
| 3. Humidity absorption ⁹⁾ | | % | 0,2 |
| 4a. Maximum permissible service temp. ⁹⁾ | UL746B | °C | 85 |
| 4b. Lower permissible service temp. ⁹⁾ | | | -15 |

II. Mechanical Properties

| | Test method | Unit | Value |
|---|-------------|-------------------|-------|
| 1. Tensile strength at yield (σ_S) | ISO 527 | MPa | 49 |
| 2. Elongation at yield (ϵ_S) | | % | 5 |
| 3. Tensile strength at break (σ_R) | | MPa | 80 |
| 4. Elongation at break (ϵ_R) | | % | 15 |
| 5. Impact strength (a_n) | ISO 179 | kJ/m ² | n.b. |
| 6. Notch impact strength (a_k) ⁹⁾ | | | 27 |
| 7. Ball indentation (H_k)/Rockwell hardness ⁹⁾ | ISO 2039 | MPa | 150 |
| 8. Shore-D | ISO 868 | | 90 |
| 9. Flexural strength (σ_B 3,5 %) ⁹⁾ | ISO 178 | MPa | 76 |
| 10. Modulus of elasticity (E) | ISO 527 | | 2570 |

III. Thermal Properties⁹⁾

| | Test method | Unit | Value |
|---|----------------------|----------------------------------|-------|
| 1. Vicat-softening point | VST/B/50 VST/A/50 | ISO 306 | 114 |
| | | | - |
| 2. Heat deflection temperature HDT/B | HDT/A | ISO 75 | - |
| | | | 105 |
| 3. Coef. of linear thermal expansion (α) | ISO 11359 | K ¹ *10 ⁻⁴ | 0,7 |
| 4. Thermal conductivity at 20 °C (λ) | ISO 22007-4 | W/(m*K) | 0,14 |
| 5. Glass transition temperature (T _m) | ISO 3146 | ISO 3146 | 110 |
| 6. Melting temperature (T _m) | | | 110 |

IV. Electrical Properties

| | Test method | Unit | Value |
|---|-------------|-------|-------------------|
| 1. Volume resistivity (ρ_D) ⁸⁾ | IEC 60093 | Ω*cm | >10 ¹³ |
| 2. Surface resistivity (R_o) ⁸⁾ | | Ω | ≥10 ¹³ |
| 3. Dielectric constant at 1MHz (ϵ_r) ⁹⁾ | IEC 60250 | - | 3 |
| 4. Dielectric loss factor at 1 MHz (tanδ) ⁹⁾ | | - | 0,01 |
| 5. Dielectric strength ⁹⁾ | IEC 60243-1 | kV/mm | 40 |
| 6. Tracking resistance ⁹⁾ | IEC 60112 | V | KB 600 |

V. Additional Data

| | Test method | Unit | Value |
|---|-------------|------|-------|
| 1. Bondability | - | - | + |
| 2. Physiological indifference ⁵⁾ according ⁹⁾ | EEC FDA | - | - |
| | | - | - |
| 3. Flammability ⁹⁾ | UL 94 | - | V-0 |
| 4. Limiting Oxygen Index (LOI) ⁹⁾ | ASTM D2863 | % | 65 |
| 5. UV stabilisation ⁶⁾ ⁹⁾ | - | - | - |

1) The physical data contained in this table are typical values and reflect the current state of our knowledge. The data are arithmetic average values which are tested by test specimens made out of rods (\varnothing 40-60 mm). These has to be understood as guidelines, and shall not be used for specification purposes for finished parts. Missing data are completed by data of the raw materials.

2) Pretreatment necessary 5) Physiological indifferences are valid for nature coloured materials on the raw material side. There are also approvals for our semi-finished products available or in preparation. Please check this separately with us.

6) valid for nature coloured materials. An additional UV protection can be taken over by special pigments e.g. carbon black.

7) Test results without UL registration 8) Data are only valid for grey coloured rods 9) Data taken from raw material *Self-assessment

n.b.= no break + = yes o = limited - = no/no data available