

Technical Data Sheet

MEDI-GEHR PP-HT MG[®]

PLASTICS ENGINEERED BY



I. Physical Properties¹⁾

	Test method	Unit	Value
1. Specific gravity (ρ)	ASTM D1505	g/cm ³	0,9
2. Water absorption ⁹⁾	ISO 62	%	-
3. Humidity absorption ⁹⁾			-
4a. Maximum permissible service temp.. ⁹⁾	UL746B	°C	100
4b. Lower permissible service temp. ⁹⁾			5

II. Mechanical Properties

	Test method	Unit	Value
1. Tensile strength at yield (σ_S)	ASTM D638	MPa	40,3
2. Elongation at yield (ϵ_S)		%	-
3. Tensile strength at break (σ_R)		MPa	-
4. Elongation at break (ϵ_R)		%	4,6
5. Impact strength (a_n) ⁹⁾	ASTM D256	J/m	-
6. Notch impact strength (a_k) ⁹⁾			21,5
7. Ball indentation (H_k)/Rockwell hardness ⁹⁾	ASTM D785	MPa	- / R 110
8. Shore-D	ISO 868		-
9. Flexural strength ($\sigma_{B 3,5\%}$) ⁹⁾	ISO 178	MPa	-
10. Modulus of elasticity (E_t)	ASTM D790		2345

III. Thermal Properties ⁹⁾

	Test method	Unit	Value
1. Vicat-softening point VST/B/50	ISO 306	°C	-
VST/A/50			-
2. Heat deflection temperature HDT/B	ASTM D648		133
HDT/A			-
3. Coef. of linear thermal expansion (α)	ISO 11359	K ⁻¹ *10 ⁻⁴	-
4. Thermal conductivity at 20 °C (λ)	ISO 22007-4	W/(m*K)	-
5. Glass transition temperature (T_g)	ASTM D3418	°C	-
6. Melting temperature (T_m)			165

IV. Electrical Properties

	Test method	Unit	Value
1. Volume resistivity (ρ_D) ⁸⁾	IEC 60093	Ω *cm	-
2. Surface resistivity (R_c) ⁸⁾		Ω	-
3. Dielectric constant at 1MHz (ϵ_r) ⁹⁾	IEC 60250	-	-
4. Dielectric loss factor at 1 MHz ($\tan\delta$) ⁹⁾		-	-
5. Dielectric strength ⁹⁾	IEC 60243-1	kV/mm	-
6. Tracking resistance ⁹⁾	IEC 60112	V	-

V. Additional Data

	Test method	Unit	Value
1. Bondability	-	-	0
2. Physiological indifference ⁵⁾ according	EEC	-	-
	FDA	-	+
3. Biocompatibility	ISO 10993	-1, -5, -12, -18 class VI	+
	USP		+
4. Flammability ⁹⁾	UL 94	-	-
5. Limiting Oxygen Index (LOI) ⁹⁾	ASTM D2863	%	-
6. UV stabilisation ^{6) 9)}	-	-	0

1) The physical data contained in this table are typical values and reflect the current state of our knowledge. The data are arithmetic average values which are tested by test specimens made out of rods (ϕ 40-60 mm). These data has to be understood as guidelines, and shall not be used for specification purposes for finished parts. Missing data are completed by data of the raw materials.

2) Pretreatment necessary 5) Physiological indifferences are valid for nature coloured materials on the raw material side. There are also approvals for our semi-finished products available or in preparation. Please check this separately with us.

6) valid for nature coloured materials. An additional UV protection can be taken over by special pigments e.g. carbon black.

7) Test results without UL registration 8) Data are only valid for natural colours 9) Data taken from raw material n.b.= no break

+ = yes o = limited - = no/no data available